



EXHIBIT A

Paper #18 H/K

**Technical Data Sheet  
5702**

TYPE : Estane® 5702 is an aromatic polyester-based polyurethane polymer.

MELTTEMPERATURE (DSC) : 79°C

MECHANICAL PROPERTIES	TEST SPECIMEN	TEST METHOD	UNIT	VALUE
Hardness	A	DIN 53505	shore A	65
Density	A	DIN 53479	g/cm <sup>3</sup>	1.18
Tensile strength	B	DIN 53504	MPa	37
Elongation			%	590
Tensile Stress at 50 % Elongation			MPa	2
100 % Elongation			MPa	2.4
300 % Elongation			MPa	4.8
Tear Resistance	B	DIN 53515	kN/m	47

(A) moulded plaques; 15 x 10 x 0,2 cm

(B) solution cast films; thickness 30-40 µ m

Solubility		
Methylethylketone	(MEK)	Soluble
Dimethylformamide	(DMF)	Soluble
Tetrahydrofuran	(THF)	Soluble
Ethylacetate		Swelling
Cyclohexanone		Soluble

**SUPPLY FORM AND STANDARD PACKAGING**

Estane® 5702 is supplied in granule form and is packaged in polyethylene bags.  
Net weight 25 kg.

**Solution viscosity specification values**

15 % total solids in methylethylketone (MEK)		
- Brookfield RVTD viscometer		
- spindle n° 2		
- 20 rpm		
- 23°C ± 1°C		
5702 F2	460 - 680	mPa.s
5702 F3	180 - 460	mPa.s

The information contained herein is believed reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. BFGoodrich shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond BFGoodrich's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

**BFGoodrich**  
Performance Materials

BFGoodrich Chemical (België) N.V.  
Verdunstraat 742, 1130 Brussel, Belgium  
Tel: +32-2-247.19.11, Fax +32-2-247.19.90